



## OKS 2351

### Aluminium Paste, Anti-Seize Paste, Spray



#### Description

Aluminium paste for assembling screw and bolt threaded connections that are subjected to high temperatures and corrosive influences.

#### Applications

- Assembly lubrication of machine parts, screw connections, fittings, flange and plug-in connections, guides, sliding and sealing surfaces of ovens, boilers, burners, motors, engines subject to high-temperature conditions
- Separating paste

#### Branches

- Glass and foundry industry
- Rubber and plastic processing
- Shipbuilding and marine technology
- Logistics
- Rail vehicle technology
- Chemical industry
- Paper and packaging industry
- Municipal services
- Plant and machine (tool) engineering
- Iron and steel industry

#### Application tips

For best adhesion, clean contamination and other lubricants from thread and slide surfaces. Best way is to clean mechanically first (for example, with a wire brush) and then with OKS 2610/OKS 2611 universal cleaning agent. Apply sufficient OKS 235 evenly to the head or nut contact surface and to the thread by using a brush, spatula, etc. Spray on OKS 2351 evenly. Do not use paste instead of grease and mix only with suitable lubricants.

#### Packaging

- 400 ml Spray

#### Advantages and benefits

- Excellently suited for preventing seizing and burning together
- Highly effective due to outstanding separating action and pressure absorption
- Good protection against ingress of splashing and condensed water
- Free of heavy metal compounds
- Good corrosion protection
- Excellent water resistance
- Wide operating temperature range
- Optimum ratio of screw tightening torque to achievable pre-tension



## PRODUCT INFORMATION

### OKS 2351

### Aluminium Paste, Anti-Seize Paste, Spray

#### Technical Data

	Standard	Conditions	Unit	Value
<b>Main components</b>				
base oil				synthetic oil
thickener				inorganic
solid lubricants				other solid lubricants
solid lubricants				aluminium powder
<b>Application related technical data</b>				
flashing point	DIN ISO 2592	> 79	°C	> 180
drop point	DIN ISO 2176		°C	without
unworked penetration	DIN ISO 2137	no shear stress	0.1 mm	310-340
lower operating temperature			°C	-40
upper operating temperature			°C	1,100
colour				metallic silver
density (at 20°C)	DIN EN ISO 3838		g/cm <sup>3</sup>	0.98
water resistance	DIN 51 807-1	40°C	Degree 1-3	1
salt spray test	DIN 50 021	layer thickness 60µm	h	> 50
thread friction coefficient (µ total)	DIN EN ISO 16 047	screw ISO 4017 M10x55-8.8 black-oxide, nut ISO 4032 M10-10 black-oxide		0.12
breakaway torque	DIN 267-27	A2-70, 400°C, 100h	Nm	< 2.0 x tightening torque

#### OKS Spezialschmierstoffe GmbH

Ganghoferstraße 47  
82216 Maisach  
Phone: +49 (0) 8142 3051 - 500  
info@oks-germany.com  
[www.oks-germany.com](http://www.oks-germany.com)



The information in this publication reflects state-of-the-art technology, as well as extensive testing and experience. Due to the diversity of possible applications and technical realities, they can only serve as recommendations and are not arbitrarily transferable. Therefore, no obligations, liability or warranty claims can be derived from them. We only accept liability for the suitability of our products for particular purposes, and for certain properties of our products, in the event that we have accepted such liability in writing in the individual case. Any case of justified warranty claims shall be limited to the delivery of replacement goods free of defects, in the event that this subsequent improvement fails, to reimbursement of the purchase price. Any and all further claims, in particular the liability for consequential injuries or damage, shall always be excluded. Prior to use, the customer must conduct its own testing to prove suitability. The data are subject to change for the sake of progress. ® = Registered trademark  
**Safety data sheet** for industrial and commercial users is available for downloading under [www.oks-germany.com](http://www.oks-germany.com). Our Customer and Technical service will be pleased to help should you have any further questions.