


# OKS 353

## High-Temperature Chain Oil, synthetic



### Description

OKS 352 is a synthetic high-temperature oil.

### Applications

- Lubrication of chains, hinges, joints, clamping and drying frames, and slideways at higher temperatures
- For conveying systems in painting, stoving, drying and cooling bed installations

### Branches

- Paper and packaging industry
- Glass and foundry industry
- Rubber and plastic processing
- Rail vehicle technology
- Shipbuilding and marine technology
- Plant and machine (tool) engineering
- Chemical industry
- Municipal services
- Logistics
- Iron and steel industry

### Advantages and benefits

- Non-contaminating liquid lubricant for higher temperatures
- Highly effective due to optimum wear protection, outstanding oxidation behaviour and good creep properties
- Absolutely resistant to water and steam, inert with respect to acidic media
- Outstanding adhesion and lubrication effect with no tendency to drip and no formation of hard residues

### Application tips

For best results clean the cold surface, first mechanically and then with OKS 2610/OKS 2611 Universal Cleaner. Apply sufficient amount onto the lubrication areas with brush, dip oiler, dipping or suitable automatic lubrication systems. Let excess drip off and let product affect before the beginning of operation. Instructions of the machine manufacturer have to be considered. Relubrication period and amount should be stated according the application conditions. Only mix with appropriate lubricants.

### Packaging

- 1 l Bottle
- 5 l Canister
- 25 l Canister

# OKS 353

## High-Temperature Chain Oil, synthetic

### Technical data

|   | Standard        | Conditions         | Unit               | Value     |
|---|-----------------|--------------------|--------------------|-----------|
| <b>Main components</b>                    |                 |                    |                    |           |
| base oil                                  |                 |                    |                    | ester     |
| <b>Application related technical data</b> |                 |                    |                    |           |
| marking                                   | DIN 51 502      |                    |                    | CLP E 100 |
| viscosity (at 40°C)                       | DIN 51 562-1    |                    | mm <sup>2</sup> /s | 100       |
| viscosity at (100°C)                      | DIN 51 562-1    |                    | mm <sup>2</sup> /s | 14        |
| viscosity index                           | DIN ISO 2909    | Process B          |                    | > 135     |
| viscosity class                           | DIN ISO 3448    | DIN 51 562-1, 40°C | ISO VG             | 100       |
| pour point                                | DIN ISO 3016    | 3°C step           | °C                 | -30       |
| flashing point                            | DIN ISO 2592    | > 79               | °C                 | > 270     |
| lower operating temperature               |                 |                    | °C                 | 0         |
| upper operating temperature               |                 |                    | °C                 | 250       |
| colour                                    |                 |                    |                    | yellow    |
| density (at 20°C)                         | DIN EN ISO 3838 |                    | g/cm <sup>3</sup>  | 0.91      |
| four-ball test rig welding load           | DIN 51 350-2    |                    | N                  | 2,000     |
| four-ball test rig wear                   | DIN 51 350-3    |                    | mm                 | 0.4       |
| FZG wear protection test                  | DIN 51 354      | A/8,3/90           | power level        | > 12      |
| <b>Properties and approvals</b>           |                 |                    |                    |           |
| UFI                                       |                 |                    |                    |           |

### OKS Spezialschmierstoffe GmbH

Ganghoferstraße 47  
 82216 Maisach  
 +49 8142 3051 - 500  
 info@oks-germany.com  
 www.oks-germany.com



The information in this publication reflects state-of-the-art technology, as well as extensive testing and experience. Due to the diversity of possible applications and technical realities, they can only serve as recommendations and are not arbitrarily transferable. Therefore, no obligations, liability or warranty claims can be derived from them. We only accept liability for the suitability of our products for particular purposes, and for certain properties of our products, in the event that we have accepted such liability in writing in the individual case. Any case of justified warranty claims shall be limited to the delivery of replacement goods free of defects, in the event that this subsequent improvement fails, to reimbursement of the purchase price. Any and all further claims, in particular the liability for consequential injuries or damage, shall always be excluded. Prior to use, the customer must conduct its own testing to prove suitability. The data are subject to change for the sake of progress. ® = Registered trademark  
**Product restricted to professional users.** Safety data sheet available for download at [www.oks-germany.com](http://www.oks-germany.com)  
 Our Customer and Technical service will be pleased to help should you have any further questions.