


OKS 260

White Assembly Paste



Description

Mounting paste for lubricating sliding points at which dark lubricants are not desired and where frictional corrosion is to be avoided.

Applications

- Assembly lubrication of sliding points
- Screw lubrication at normal temperatures and low speeds
- Lubrication when joining parts

Branches

- Plant and machine (tool) engineering
- Paper and packaging industry
- Glass and foundry industry
- Iron and steel industry
- Shipbuilding and marine technology
- Municipal services
- Logistics
- Rubber and plastic processing
- Rail vehicle technology
- Chemical industry

Advantages and benefits

- Prevents frictional corrosion on joint connections of steel parts of all kinds subject to vibration loading under damp-room and aggressive operating conditions
- Low consumption thanks to thin-film lubrication
- Excellent water resistance
- Excellent lubricating and separating effect
- Good corrosion protection behaviour
- Metal-free

Application tips

For optimum adhesion, clean contamination and other lubricants from sliding surfaces. Best way is to clean mechanically first (for example, with a wire brush) and then with OKS 2610/OKS 2611 universal cleaner. Apply the paste evenly and thinly with a brush, spatula, etc. Remove excesses. Do not use paste instead of grease and mix only with suitable lubricants.

Packaging

- 250 g Can
- 1 kg Can
- 5 kg Hobbock
- 25 kg Hobbock

OKS 260 White Assembly Paste

Technical data

	Standard	Conditions	Unit	Value
Main components				
base oil				white oil
thickener				lithium soap
solid lubricants				white solid lubricants
Application related technical data				
viscosity (at 40°C)	DIN 51 562-1		mm ² /s	22
flashing point	DIN ISO 2592		°C	195
unworked penetration	DIN ISO 2137	no shear stress	0.1 mm	250-280
lower operating temperature			°C	-25
upper operating temperature			°C	150
colour				light-coloured
density (at 20°C)	DIN EN ISO 3838		g/cm ³	1.25
water resistance	DIN 51 807-1	3h/90°C	Degree	0-90
four-ball test rig welding load	DIN 51 350-4		N	2,600
Total friction coefficient (μ)	DIN EN ISO 16 047	screw ISO 4017 M10x55-8.8 black-oxide, nut ISO 4032 M10-10 black-oxide		0.08
press-fit test (μ)	draft DIN 51 833			0,09, no chatter
Properties and approvals				
UFI				7NMC-M0A6-J00U-Y3QJ

OKS Spezialschmierstoffe GmbH

Ganghoferstraße 47

82216 Maisach

+49 8142 3051 - 500

info@oks-germany.com

www.oks-germany.com

a brand of
 **FREUDENBERG**

The information in this publication reflects state-of-the-art technology, as well as extensive testing and experience. Due to the diversity of possible applications and technical realities, they can only serve as recommendations and are not arbitrarily transferable. Therefore, no obligations, liability or warranty claims can be derived from them. We only accept liability for the suitability of our products for particular purposes, and for certain properties of our products, in the event that we have accepted such liability in writing in the individual case. Any case of justified warranty claims shall be limited to the delivery of replacement goods free of defects, in the event that this subsequent improvement fails, to reimbursement of the purchase price. Any and all further claims, in particular the liability for consequential injuries or damage, shall always be excluded. Prior to use, the customer must conduct its own testing to prove suitability. The data are subject to change for the sake of progress. ® = Registered trademark
Product restricted to professional users. Safety data sheet available for download at www.oks-germany.com
Our Customer and Technical service will be pleased to help should you have any further questions.