




OKS 471

White Universal High-Performance Grease, Spray





Description

Universal grease with white solid lubricants.

Applications

- Lubrication of normal-load friction, rolling and pivoting bearings
- · Lubrication of spindles and guides at machines
- Lubrication of moving parts at fine-mechanical devices as well as household appliances

Branches

- · Iron and steel industry
- Municipal services
- · Plant and machine (tool) engineering
- Chemical industry
- Paper and packaging industry
- · Shipbuilding and marine technology
- · Rubber and plastic processing
- · Glass and foundry industry
- · Logistics
- Rail vehicle technology

Application tips

Clean the lubricating points well for optimal effect. Before filling for first time, remove anti-corrosion agent. Fill the bearing such that all functional surfaces are certain of being greased. Fill normal bearings up to about 1/3 of the free space inside the bearing. Low-speed bearings (DN value below 50,000) and their housings should be filled completely. In as far as available, the bearing and machine manufacturer's instructions should be observed. Subsequent lubrication at the lubrication nipples by grease gun or by automatic lubrication system. Assess the lubrication frequency and quantity on the basis of the service conditions. If old grease cannot be removed, restrict the quantity of grease so as to avoid over-lubricating the bearing. If lubrication frequencies tend to be low, you should aim for a full grease change. Caution: Only mix with suitable lubricants.

Packaging

400 ml Spray

Advantages and benefits

- Lubrication when dark-coloured lubricants cannot be used
- Saving of maintenance and lubricant costs by reducing downtimes and corrective maintenance
- · Waterproof











OKS 471

White Universal High-Performance Grease, Spray

Technical data

	Standard	Conditions	Unit	Value
Main components	•		<u> </u>	
base oil				mineral oil
thickener				lithium hydroxystearate
solid lubricants				white solid lubricants
Application related technical	al data			
marking	DIN 51 502	DIN 51 825		KF2K-30
viscosity (base oil)	DIN 51 562-1	at 40°C	mm²/s	approx. 110
viscosity (base oil)	DIN 51 562-1	at 100°C	mm²/s	approx. 10
drop point	DIN ISO 2176		°C	> 195
consistency	DIN 51 818	DIN ISO 2137	NLGI grade	2
worked penetration	DIN ISO 2137	60DH	0.1 mm	265-295
oil separation	DIN 51 817	168h/40°C	percent in weight	< 5
lower operating temperature	DIN 51 805	≤ 1,400 hPa	°C	-30
upper operating temperature	DIN 51 821-2	F50 (A/1500/6000), 100h	°C	120
colour				white
density	DIN EN ISO 3838	at 20°C	g/cm³	0.72
water resistance	DIN 51 807-1	90°C	Degree	1-90
DN value (dm x n)			mm/min	300,000
four-ball test rig welding load	DIN 51 350-4		N	3,600
four-ball test rig wear	DIN 51 350-5	1h, 800N	mm	< 1.4
SKF-EMCOR	DIN 51 802	168h, distilled water	corr. degree	1
SKF-EMCOR Copper	DIN 51 811	24h, 100°C	corr. degree	1-100
Properties and approvals				
UFI				NA0H-90VE-G00R-4GEG

OKS Spezialschmierstoffe GmbH

Ganghoferstraße 47 82216 Maisach

4 +49 8142 3051 - 500

☑ info@oks-germany.com

★ www.oks-germany.com





The information in this publication reflects state-of-the-art technology, as well as extensive testing and experience. Due to the diversity of possible applications and technical realities, they can only serve as recommendations and are not arbitrarily transferable. Therefore, no obligations, liability or warranty claims can be derived from them. We only accept liability for the suitability of our products for particular purposes, and for certain properties of our products, in the event that we have accepted such liability in writing in the individual case. Any case of justified warranty claims shall be limited to the delivery of replacement goods free of defects, in the event that this subsequent improvement fails, to reimbursement of the purchase price. Any and all further claims, in particular the liability for consequential injuries or damage, shall always be excluded. Prior to use, the customer must conduct its own testing to prove suitability. The data are subject to change for the sake of progress. * = Registered trademark

Product restricted to professional users. Safety data sheet available for download at www.oks-germany.com Our Customer and Technical service will be pleased to help should you have any further questions.





