



# OKS 340

## Chain Protector, highly adhesive



**Mo<sub>x</sub>-Active**

### Description

Synthetic lubricant for indoor and outdoor machine elements subjected to high pressure or corrosive influences.

### Applications

- Lubrication of fast-running drive chains of all designs for open or semi-open operation without a permanent re-lubricating device, such as motorcycle and bicycle chains
- Lubrication of hoisting chains such as multirow roller chains or stacker truck chains, as well as single or multiple flat-link articulated chains

### Branches

- Logistics
- Chemical industry
- Municipal services
- Shipbuilding and marine technology
- Paper and packaging industry
- Rubber and plastic processing
- Plant and machine (tool) engineering
- Rail vehicle technology
- Glass and foundry industry
- Iron and steel industry

### Advantages and benefits

- Highly effective due to outstanding creep and gap penetration properties
- Extreme adhesive strength
- Extreme wear protection through Mo<sub>x</sub>-Active additive
- Very high resistance to cold and hot water as well as to saline solutions
- Excellent corrosion protection
- O-ring neutral
- Also available as spray version OKS 341

### Application tips

For best adhesion, clean the surfaces mechanically first and then with OKS 2610/OKS 2611 universal cleaner. Apply OKS 340 with a brush, drip oiler, by immersion or using a suitable automatic lubrication system. Allow excess to drip off and wait for lubricant to penetrate before resuming operation. In as far as available, observe the machine manufacturer's instructions. Assess the lubrication frequencies and quantities on basis of service conditions, avoid excesses. Caution: Only mix with suitable lubricants.

### Packaging

- 1 l Bottle
- 5 l Canister
- 25 l Canister
- 200 l Drum

# OKS 340

## Chain Protector, highly adhesive

### Technical data

	Standard	Conditions	Unit	Value
<b>Main components</b>				
base oil				polyisobutylene
additives				adhesion improver
additives				Mo <sub>x</sub> -Active
<b>Application related technical data</b>				
marking	DIN 51 502			CLP X 460
viscosity	DIN 51 562-1	at 40°C	mm <sup>2</sup> /s	440
viscosity class	DIN ISO 3448	DIN 51 562-1, 40°C	ISO VG	460
flashing point	DIN ISO 2592	> 79	°C	> 200
lower operating temperature			°C	-30
upper operating temperature			°C	180
colour				greenish
density	DIN EN ISO 3838	at 20°C	g/cm <sup>3</sup>	0.88
four-ball test rig welding load	DIN 51 350-2		N	2,600
<b>Properties and approvals</b>				
UFI				NQS1-T0N4-N000-CHVD

**Klüber Lubrication München GmbH & Co. KG**  
Geisenhausenerstraße 7 / 81379 München /  
Germany / phone +49 89 7876-0

The data in this document is based on our general experience and knowledge at the time of publication and is intended to give information of possible applications to a reader with technical experience. It constitutes neither an assurance of product properties nor does it release the user from the obligation of performing preliminary field tests with the product selected for a specific application. All data are guide values which depend on the lubricant's composition, the intended use and the application method. The technical values of lubricants change depending on the mechanical, dynamical, chemical and thermal loads, time and pressure. These changes may affect the function of a component. We recommend contacting us to discuss your specific application. If possible we will be pleased to provide a sample for testing on request. Klüber products are continually improved. Therefore, Klüber Lubrication reserves the right to change all the technical data in this document at any time without notice.