


# OKS 1140

## Extreme-Temperature Silicone Grease



### Description

OKS 1140 is an extreme-temperature silicone grease for slow-running machine elements at extremely high temperatures.

### Applications

- Lubrication of slow-running rolling and friction bearings, rollers, transport chains or sliding surfaces on kiln trolleys, bakery machines, drying tunnels, foundry machines, boiler firing systems, plastics processing machines for welding and soldering machines etc.

### Branches

- Shipbuilding and marine technology
- Plant and machine (tool) engineering
- Rubber and plastic processing
- Logistics
- Paper and packaging industry
- Chemical industry
- Glass and foundry industry
- Rail vehicle technology
- Municipal services
- Iron and steel industry

### Advantages and benefits

- Highly effective due to optimum temperature-stable silicone grease formula
- Excellently suited for grease lubricating points subject to high-temperature loading
- Broad range of uses outside normal grease performance areas

### Application tips

For best results, clean lubricant points and surfaces carefully, e.g. with OKS 2610 or OKS 2611 universal cleaner. Remove the corrosion protection ahead of the initial filling. Fill the bearings in a way that all the functional surfaces for sure get the grease. Slow moving bearings(DN-value < 50,000) should be filled completely, normal moving bearings should be filled to 1/3 of the free inner housing space. Observe the instructions of the bearing or machine manufacturer. Relubrication with a grease gun on to the grease nipples or with an automatic lubrication system. Relubrication intervals and amount to be defined acc. to the service conditions. If the removal of the old grease is not possible the amount of grease has to be limited to avoid excess lubrication of the bearing. At longer relubrication intervals a complete exchange of the old grease is recommended. Only mix with appropriate lubricants. Bearings filled with silicon grease must not have higher loads than 1/3rd of the bearing's permitted load. Silicone-based plastics, e.g. silicone rubber, can be dissolved by silicone grease. Silicone grease must not be applied to sliding surfaces under influence of pure oxygen.

# OKS 1140

## Extreme-Temperature Silicone Grease

### Packaging

- 500 g Can
- 5 kg Hobbock
- 25 kg Hobbock

### Technical data

	Standard	Conditions	Unit	Value
<b>Main components</b>				
base oil				polyphenylmethylsiloxane
thickener				special carbon black
<b>Application related technical data</b>				
marking				KFSI2U-20
viscosity (at 40°C)	DIN 51 562-1	base oil	mm <sup>2</sup> /s	100
flashing point	DIN ISO 2592	> 79	°C	> 250
drop point	DIN ISO 2176		°C	without
consistency	DIN 51 818	DIN ISO 2137	NLGI grade	2
worked penetration	DIN ISO 2137	60DH	0.1 mm	265-295
oil separation	DIN 51 817	18h/40°C	percent in weight	1
lower operating temperature	DIN 51 805	≤ 1,400 hPa	°C	-20
upper operating temperature			°C	290
maximal operating temperature			°C	300
colour				black
density (at 20°C)	DIN EN ISO 3838		g/cm <sup>3</sup>	1.03
water resistance	DIN 51 807-1	90°C	Degree	0
DN value (dm x n)			mm/min	75,000
four-ball test rig welding load	DIN 51 350-4		N	2,100
four-ball test rig wear	DIN 51 350-5	1.420/min, 1h, 400N	mm	1.2
SKF-EMCOR	DIN 51 802		corr. degree	2-2
<b>Product specific technical data</b>				
evaporation loss	DIN 58 397-1	24h, 160°C	percent in weight	1
<b>Properties and approvals</b>				
UFI				

### OKS Spezialschmierstoffe GmbH

Ganghoferstraße 47

82216 Maisach

☎ +49 8142 3051 - 500

✉ info@oks-germany.com

🏠 www.oks-germany.com

a brand of  


The information in this publication reflects state-of-the-art technology, as well as extensive testing and experience. Due to the diversity of possible applications and technical realities, they can only serve as recommendations and are not arbitrarily transferable. Therefore, no obligations, liability or warranty claims can be derived from them. We only accept liability for the suitability of our products for particular purposes, and for certain properties of our products, in the event that we have accepted such liability in writing in the individual case. Any case of justified warranty claims shall be limited to the delivery of replacement goods free of defects, in the event that this subsequent improvement fails, to reimbursement of the purchase price. Any and all further claims, in particular the liability for consequential injuries or damage, shall always be excluded. Prior to use, the customer must conduct its own testing to prove suitability. The data are subject to change for the sake of progress. ® = Registered trademark  
**Product restricted to professional users.** Safety data sheet available for download at [www.oks-germany.com](http://www.oks-germany.com)  
Our Customer and Technical service will be pleased to help should you have any further questions.