


OKS 277

High-Pressure Lubrication Paste, with PTFE



Description

High-pressure lubrication paste with PTFE for the lubrication of sliding machine elements made of metal, plastic and ceramic.

Applications

- Lubricating and sealing off tap cocks, labyrinth seals, stuffing boxes and packings
- Lubricating and sealing off fittings made of metal, plastic and ceramic, e.g. drain, cold- and hot-water fittings
- Long-term lubrication of heavily loaded press and guide plates, for example on telescope booms of mobile cranes
- As a lubricant for of threaded spindles on radiator thermostats

Advantages and benefits

- Reduces wear
- Extension of the relubrication intervals
- High resistance to oxidation
- Noise and vibration-damping
- Resistant to cold and hot water, water vapour, lactic, formic, acetic and fruit acid, as well as alkaline and acidic cleaning agents and disinfectants
- Good elastomer and plastic compatibility

Branches

- Plant and machine (tool) engineering
- Glass and foundry industry
- Iron and steel industry
- Rail vehicle technology
- Rubber and plastic processing
- Paper and packaging industry
- Chemical industry
- Municipal services
- Logistics
- Shipbuilding and marine technology

Application tips

For optimum adhesion, clean contamination and other lubricants from slide surfaces. Best way is to clean mechanically first and then with OKS 2610/OKS 2611 universal cleaner. Apply sufficient paste evenly with a brush, spatula, etc. The paste will also act as a sealant. Do not use paste instead of grease and mix only with suitable lubricants.

Packaging

- 1 kg Can
- 25 kg Hobbock

OKS 277

High-Pressure Lubrication Paste, with PTFE

Technical data

	Standard	Conditions	Unit	Value
Main components				
base oil				ester
thickener				PTFE
Application related technical data				
viscosity (base oil)	DIN 51 562-1	at 40°C	mm²/s	5,000
viscosity (base oil)	DIN 51 562-1	at 100°C	mm²/s	340
drop point	DIN ISO 2176		°C	without
unworked penetration	DIN ISO 2137	no shear stress	0.1 mm	220-250
lower operating temperature			°C	-20
upper operating temperature			°C	150
colour				white
density	DIN 51 757	at 20°C	g/cm³	1.2
four-ball test rig welding load	DIN 51 350-4		N	2,200

OKS Spezialschmierstoffe GmbH

Ganghoferstraße 47

82216 Maisach

☎ +49 8142 3051 - 500

✉ info@oks-germany.com

🏠 www.oks-germany.com

a brand of
 **FREUDENBERG**

The information in this publication reflects state-of-the-art technology, as well as extensive testing and experience. Due to the diversity of possible applications and technical realities, they can only serve as recommendations and are not arbitrarily transferable. Therefore, no obligations, liability or warranty claims can be derived from them. We only accept liability for the suitability of our products for particular purposes, and for certain properties of our products, in the event that we have accepted such liability in writing in the individual case. Any case of justified warranty claims shall be limited to the delivery of replacement goods free of defects, in the event that this subsequent improvement fails, to reimbursement of the purchase price. Any and all further claims, in particular the liability for consequential injuries or damage, shall always be excluded. Prior to use, the customer must conduct its own testing to prove suitability. The data are subject to change for the sake of progress. ® = Registered trademark
Product restricted to professional users. Safety data sheet available for download at www.oks-germany.com
Our Customer and Technical service will be pleased to help should you have any further questions.