



# OKS 310

## MoS<sub>2</sub> High-Temperature Lubricant



### Description

OKS 310 is a high-temperature oil with MoS<sub>2</sub> for lubrication of machine elements up to +450°C.

### Applications

- Lubrication of friction and rolling bearings, chains, joints or slideways at higher temperatures
- For conveying systems under radiation heat in painting, stoving and drying systems, travelling grates in firing systems
- Dry lubrication at temperatures above 200°C
- Lubrication of elastomers and plastics not resistant to mineral oil

### Advantages and benefits

- Highly suitable as a high-temperature lubricant
- Very effective due to finest, homogeneous MoS<sub>2</sub> distribution in the oil
- Resistant to water and many chemicals, fuels, lubricants and hydraulic oils

### Branches

- Chemical industry
- Glass and foundry industry
- Rubber and plastic processing
- Rail vehicle technology
- Municipal services
- Plant and machine (tool) engineering
- Iron and steel industry
- Logistics
- Paper and packaging industry
- Shipbuilding and marine technology

### Application tips

For best adhesion, clean the surfaces. Best way is to clean mechanically first and then with OKS 2610/OKS 2611 universal cleaner. With a brush, drip oiler or by immersion or using a suitable automatic lubrication system, apply a sufficient quantity to the locations to be lubricated. If at all possible, avoid excess. Observe the machine manufacturer's instructions. Assess the lubrication frequency and quantity on basis of service conditions. Only mix with suitable lubricants.

### Packaging

- 1 l Bottle
- 5 l Canister
- 25 l Canister

OKS 310

MoS<sub>2</sub> High-Temperature Lubricant

Technical data

	Standard	Conditions	Unit	Value
Main components				
base oil				polyglycol
solid lubricants				MoS <sub>2</sub>
Application related technical data				
viscosity at (40°C)	DIN 51 562-1		mm²/s	150
viscosity at (100°C)	DIN 51 562-1		mm²/s	27.2
viscosity index	DIN ISO 2909			220
viscosity class	DIN ISO 3448	DIN 51 562-1, 40°C	ISO VG	100
flashing point	DIN ISO 2592	> 79	°C	240
upper operating temperature		liquid lubrication	°C	200
maximal operating temperature		dry lubrication	°C	450
colour				black
density (at 20°C)	DIN EN ISO 3838		g/cm³	1
four-ball test rig welding load	DIN 51 350-2		N	2,800
four-ball test rig wear	DIN 51 350-3		mm	0.6

OKS Spezialschmierstoffe GmbH  
Ganghoferstraße 47  
82216 Maisach  
☎ +49 8142 3051 - 500  
✉ info@oks-germany.com  
🏠 www.oks-germany.com

a brand of  
 FREUDENBERG

The information in this publication reflects state-of-the-art technology, as well as extensive testing and experience. Due to the diversity of possible applications and technical realities, they can only serve as recommendations and are not arbitrarily transferable. Therefore, no obligations, liability or warranty claims can be derived from them. We only accept liability for the suitability of our products for particular purposes, and for certain properties of our products, in the event that we have accepted such liability in writing in the individual case. Any case of justified warranty claims shall be limited to the delivery of replacement goods free of defects, in the event that this subsequent improvement fails, to reimbursement of the purchase price. Any and all further claims, in particular the liability for consequential injuries or damage, shall always be excluded. Prior to use, the customer must conduct its own testing to prove suitability. The data are subject to change for the sake of progress. ® = Registered trademark  
**Product restricted to professional users.** Safety data sheet available for download at [www.oks-germany.com](http://www.oks-germany.com)  
Our Customer and Technical service will be pleased to help should you have any further questions.