


## OKS 3751

### Adhesive Lubricant with PTFE, Spray



#### Description

Fully synthetic high-performance oil with PTFE and excellent adhesive properties.

#### Applications

- For lubricating machine elements under high loads (also under water influence)
- Lubrication of chains, joints and guides
- Lubrication of rolling and friction bearings
- Lubrication of toothed gearings, fittings, hinges and locks

#### Branches

- Catering equipment and food processing technology
- Paper and packaging industry
- Municipal services
- Glass and foundry industry
- Chemical industry
- Rubber and plastic processing
- Rail vehicle technology
- Logistics
- Plant and machine (tool) engineering
- Shipbuilding and marine technology

#### Advantages and benefits

- NSF H1 registered
- The optimal additives allow good resistance to oxidation and ageing for long operating and durability
- Resistant to cold and hot water, steam and alkaline and acidic disinfectants and cleaning agents
- Duolabel
- MOSH/MOAH-free (as per recipe)

#### Application tips

Clean the lubricating point for optimal effect. Spray on evenly OKS 3751 spray. Shake the can before use until the stirring balls can be heard. In as far as available, observe the machine manufacturer's instructions. Assess the lubrication frequency and quantity on the basis of the service conditions. Caution: Only mix with suitable lubricants.

#### Packaging

- 400 ml Spray

## OKS 3751

### Adhesive Lubricant with PTFE, Spray

#### Technical data

	Standard	Conditions	Unit	Value
<b>Main components</b>				
base oil				polyalphaolefine
solid lubricants				PTFE
<b>Application related technical data</b>				
marking	DIN 51 502	DIN 51 825		CLPF HC 100
viscosity (at 40°C)	DIN 51 562-1		mm²/s	100
viscosity at (100°C)	DIN 51 562-1		mm²/s	13.0
viscosity class	DIN ISO 3448	DIN 51 562-1, 40°C	ISO VG	100
pour point	DIN ISO 3016	3°C step	°C	< -40
flashing point	DIN ISO 2592	> 79	°C	> 240
lower operating temperature			°C	-35
upper operating temperature			°C	180
colour				whitish
density (at 20°C)	DIN EN ISO 3838		g/cm³	0.68
four-ball test rig welding load	DIN 51 350-2		N	3,000
four-ball test rig wear	DIN 51 350-3/B		mm	0.4
<b>Properties and approvals</b>				
UFI				QFE1-H074-H005-QTHX
approval for food processing technology				<a href="#">NSF H1, Reg.-Nr. 124801</a>

#### OKS Spezialschmierstoffe GmbH

Ganghoferstraße 47

82216 Maisach

+49 8142 3051 - 500

info@oks-germany.com

www.oks-germany.com

a brand of  
**FREUDENBERG**

The information in this publication reflects state-of-the-art technology, as well as extensive testing and experience. Due to the diversity of possible applications and technical realities, they can only serve as recommendations and are not arbitrarily transferable. Therefore, no obligations, liability or warranty claims can be derived from them. We only accept liability for the suitability of our products for particular purposes, and for certain properties of our products, in the event that we have accepted such liability in writing in the individual case. Any case of justified warranty claims shall be limited to the delivery of replacement goods free of defects, in the event that this subsequent improvement fails, to reimbursement of the purchase price. Any and all further claims, in particular the liability for consequential injuries or damage, shall always be excluded. Prior to use, the customer must conduct its own testing to prove suitability. The data are subject to change for the sake of progress. ® = Registered trademark  
**Product restricted to professional users.** Safety data sheet available for download at [www.oks-germany.com](http://www.oks-germany.com)  
Our Customer and Technical service will be pleased to help should you have any further questions.