



OKS 350

MoS₂ High-Temperature Chain Oil, synthetic



Description

OKS 350 is a synthetic silicone-free high-temperature chain oil with MoS₂ for machine elements and loads.

Applications

- Lubrication of chains, fringe bearings, hinges, joints, clamping and drying frames or slideways at higher temperatures and loads
- For conveying systems under radiation heat in painting, stoving and drying systems

Advantages and benefits

- Highly effective due to finest, homogeneous MoS₂ distribution in the oil
- Emergency running properties through MoS₂ at dry running
- Outstanding adhesion and lubrication effect with no tendency to drip or dry out
- Silicone-free

Branches

- Glass and foundry industry
- Rubber and plastic processing
- Shipbuilding and marine technology
- Municipal services
- Paper and packaging industry
- Plant and machine (tool) engineering
- Logistics
- Rail vehicle technology
- Iron and steel industry
- Chemical industry

Application tips

For best adhesion, clean the surfaces. Best way is to clean mechanically first and then with OKS 2610 or OKS 2611 universal cleaner. With a brush, drip oiler or by immersion or using a suitable automatic lubrication system, apply a sufficient quantity to the locations to be lubricated. Allow excess to drip off. Allow OKS 350 to soak in before operating. Observe the machine manufacturer's instructions. Assess the lubrication frequency and quantity on basis of service conditions, avoid excessive lubrication. Only mix with suitable lubricants.

Packaging

- 5 l Canister
- 25 l Canister
- 200 l Drum

OKS 350

MoS₂ High-Temperature Chain Oil, synthetic

Technical data

| | Standard | Conditions | Unit | Value |
|---|-----------------|----------------------------------|--------------------|-------------------------|
| Main components | | | | |
| base oil | | | | synthetic oil |
| solid lubricants | | | | MoS ₂ |
| additives | | | | Mo _x -Active |
| Application related technical data | | | | |
| viscosity (at 40°C) | DIN 51 562-1 | | mm ² /s | 250 |
| viscosity at (100°C) | DIN 51 562-1 | | mm ² /s | 27.5 |
| viscosity index | DIN ISO 2909 | | | 145 |
| viscosity class | DIN ISO 3448 | DIN 51 562-1, 40°C | ISO VG | 220 |
| pour point | DIN ISO 3016 | 3°C step | °C | -30 |
| flashing point | DIN ISO 2592 | > 79 | °C | > 250 |
| lower operating temperature | | | °C | -30 |
| upper operating temperature | | | °C | 250 |
| colour | | | | black |
| density (at 20°C) | DIN EN ISO 3838 | | g/cm ³ | 0.9 |
| coefficient of friction SRV (μ) | DIN 51 834-2 | 50°C, 300N, 0.5mm, 50Hz, 120 min | | 0.125 |
| wear SRV | DIN 51 834-2 | 50°C, 300N, 0.5mm, 50Hz, 120 min | mm ³ | 0.0017 |
| Properties and approvals | | | | |
| UFI | | | | |

OKS Spezialschmierstoffe GmbH

Ganghoferstraße 47
 82216 Maisach
 +49 8142 3051 - 500
 info@oks-germany.com
 www.oks-germany.com



The information in this publication reflects state-of-the-art technology, as well as extensive testing and experience. Due to the diversity of possible applications and technical realities, they can only serve as recommendations and are not arbitrarily transferable. Therefore, no obligations, liability or warranty claims can be derived from them. We only accept liability for the suitability of our products for particular purposes, and for certain properties of our products, in the event that we have accepted such liability in writing in the individual case. Any case of justified warranty claims shall be limited to the delivery of replacement goods free of defects, in the event that this subsequent improvement fails, to reimbursement of the purchase price. Any and all further claims, in particular the liability for consequential injuries or damage, shall always be excluded. Prior to use, the customer must conduct its own testing to prove suitability. The data are subject to change for the sake of progress. ® = Registered trademark
Product restricted to professional users. Safety data sheet available for download at www.oks-germany.com
 Our Customer and Technical service will be pleased to help should you have any further questions.