





OKS 1361

Silicone Release Agent, Spray





Description

Colourless parting agent and lubricant on silicone oil basis.

Applications

- Parting agent for casting, injection moulding, blow moulding and extrusion processes of plastics and elastomers
- Prevents sticking, for example of excess adhesive and sealant
- Eliminates creaking and squeaking noises when surfaces made of plastics, elastomers and metals rub on each other
- For easy fitting of plastic and rubber profiles, e.g. in door and window construction
- Lubricant for cutting edges of paper, cardboard, veneer or textile machines, etc.

Branches

- · Catering equipment and food processing technology
- · Shipbuilding and marine technology
- · Plant and machine (tool) engineering
- Rubber and plastic processing
- Paper and packaging industry
- · Chemical industry
- Glass and foundry industry
- · Municipal services
- · Maintenance and servicing
- · Iron and steel industry
- Logistics
- Rail vehicle technology

Application tips

Clean the surfaces for optimal effect. Spray on thinly and evenly. Avoid excesses. Caution: Only mix with suitable lubricants. Plastic based on silicone, such as silicone rubber can be attacked by silicone oil. Silicone may not be used at sliding points under pure oxygen.

Advantages and benefits

- NSF H1 registered
- Highly effective due to outstanding surface wetting and formation of separating film with antistatic properties
- Broad range of uses for long-term lubrication, protection, care and impregnation of material surfaces made of metal, plastic and rubber
- Minimal consumption through formation of extremely thin films
- · Resistant to water and weathering
- · Long spray tube for precision application
- MOSH/MOAH-free (as per recipe)











OKS 1361

Silicone Release Agent, Spray

Packaging

· 400 ml Spray

Technical data

	Standard	Conditions	Unit	Value
Main components				
base oil				polydimethylsiloxane
Application related technical da	ıta			
viscosity	DIN 51 562-1	at 25°C	mm²/s	350
pour point	DIN ISO 3016	3°C step	°C	-55
flashing point	DIN ISO 2592	> 79	°C	> 300
lower operating temperature			°C	-50
upper operating temperature			°C	200
colour				colourless
density	DIN EN ISO 3838	at 20°C	g/cm³	0.6
Properties and approvals				
UFI				M531-S0DG-R00S-AUM6
approval for food processing technology				NSF H1, RegNr. 129481


OKS Spezialschmierstoffe GmbH

Ganghoferstraße 47 82216 Maisach

4 +49 8142 3051 - 500

☑ info@oks-germany.com

★ www.oks-germany.com





The information in this publication reflects state-of-the-art technology, as well as extensive testing and experience. Due to the diversity of possible applications and technical realities, they can only serve as recommendations and are not arbitrarily transferable. Therefore, no obligations, liability or warranty claims can be derived from them. We only accept liability for the suitability of our products for particular purposes, and for certain properties of our products, in the event that we have accepted such liability in writing in the individual case. Any case of justified warranty claims shall be limited to the delivery of replacement goods free of defects, in the event that this subsequent improvement fails, to reimbursement of the purchase price. Any and all further claims, in particular the liability for consequential injuries or damage, shall always be excluded. Prior to use, the customer must conduct its own testing to prove suitability. The data are subject to change for the sake of progress. * e Registered trademark

*Product restricted to professional users. Safety data sheet available for download at www.oks-germany.com

Product restricted to professional users. Safety data sheet available for download at www.oks-germany.com Our Customer and Technical service will be pleased to help should you have any further questions.





