




### **OKS 2561**

# **Zinc-Aluminium Protection, Spray**



#### Description

Corrosion protection for all ferrous metals based on high-purity zinc and aluminium powder with active cathodic corrosion protection.

#### **Applications**

- For touching up damaged spots on galvanised surfaces, e.g. after welding, drilling or cutting without a subsequent paint finish
- For protecting metal surfaces such as gratings, fences, gutters and similar.

#### **Branches**

- · Rail vehicle technology
- · Logistics
- · Municipal services
- · Rubber and plastic processing
- · Shipbuilding and marine technology
- Iron and steel industry
- Chemical industry
- · Plant and machine (tool) engineering
- · Paper and packaging industry
- · Maintenance and servicing
- · Glass and foundry industry

#### Advantages and benefits

- Enduring corrosion protection with active cathodic corrosion protection thanks to optimum combination between zinc and aluminium pigments
- Colour tone resembles that of a hot-dip galvanized surface, allowing for touch-ups in a single application
- Self-healing polymer layer which closes again after slight damage and prevents corrosion
- Suitable for corrosion protection up to Category C4H as per EN ISO 12944:2018-06 for areas with an industrial atmosphere and coastal areas with moderate salt levels

#### **Application tips**

Clean the surfaces for optimum adhesion. It is best to clean mechanically first and then with OKS 2610 or OKS 2611 universal cleaner. The surface to be treated must be dry, uncoated and free of grease. Shake the can before use until you can hear the stirring balls rattle and continue shaking vigorously for 2 more minutes. Optimal layer thickness: Spray evenly onto the prepared surface from a distance of 20 - 30 cm using 3 - 4 cross coats or circular movements. Avoid local excesses. For thicker layers, apply another coat after the solvent has evaporated. After spraying, turn the can upside down and spray the valve in this position until only solvent comes out. Drying and curing times as per following technical data.

### **Packaging**

400 ml Spray











# **OKS 2561**

# **Zinc-Aluminium Protection, Spray**

#### **Technical data**

	Standard	Conditions	Unit	Value
Main components				
binder				epoxy resin
solvent				solvent mixture
solid lubricants				Zinc powder
solid lubricants				aluminium powder
Application related technical	al data			
lower operating temperature			°C	-70
upper operating temperature			°C	250
optimal layer thickness	DIN EN ISO 2178/2360	DIN 50 982-2	μm	60-80
surface covering		layer thickness 70 μm	m²/can	approx. 2
processing temperature			°C	10-35
drying time		20°C	min	5-10
curing time		at 20°C	h	12-24
curing time		at 150°C	min	15
colour				aluminium-coloured
density (at 20°C)	DIN EN ISO 3838		g/cm³	0.69
salt spray test	DIN EN ISO 9227	layer thickness >70 μm air-drying	h	>800
salt spray test	DIN EN ISO 9227	layer thickness >100 μm heat-curing (150°C/15min)	h	>1,300
Cross-cutting test	DIN EN ISO 2409	Grid spacing of 2 mm		GT=0
Properties and approvals	·			
UFI				VKQD-H0Y0-J009-8XW1

### **OKS Spezialschmierstoffe GmbH**

Ganghoferstraße 47 82216 Maisach

**4** +49 8142 3051 - 500

☑ info@oks-germany.com

★ www.oks-germany.com





The information in this publication reflects state-of-the-art technology, as well as extensive testing and experience. Due to the diversity of possible applications and technical realities, they can only serve as recommendations and are not arbitrarily transferable. Therefore, no obligations, liability or warranty claims can be derived from them. We only accept liability for the suitability of our products for particular purposes, and for certain properties of our products, in the event that we have accepted such liability in writing in the individual case. Any case of justified warranty claims shall be limited to the delivery of replacement goods free of defects, in the event that this subsequent improvement fails, to reimbursement of the purchase price. Any and all further claims, in particular the liability for consequential injuries or damage, shall always be excluded. Prior to use, the customer must conduct its own testing to prove suitability. The data are subject to change for the sake of progress. \*\* = Registered trademark\*\*

Product restricted to professional users. Safety data sheet available for download at www.oks-germany.com Our Customer and Technical service will be pleased to help should you have any further questions.





