



OKS 341

Chain Protector, highly adhesive, Spray



Mo_x-Active

Description

Synthetic lubricant for indoor and outdoor machine elements subjected to high pressure or corrosive influences.

Applications

- Lubrication of fast-running drive chains of all designs for open or semi-open operation without a permanent re-lubricating device, such as motorcycle and bicycle chains
- Lubrication of hoisting chains such as multirow roller chains or stacker truck chains, as well as single or multiple flat-link articulated chains

Branches

- Glass and foundry industry
- Logistics
- Chemical industry
- Rail vehicle technology
- Paper and packaging industry
- Rubber and plastic processing
- Shipbuilding and marine technology
- Iron and steel industry
- Municipal services
- Plant and machine (tool) engineering

Advantages and benefits

- Highly effective due to outstanding creep and gap penetration properties
- Extreme adhesive strength
- Extreme wear protection through Mo_x-Active additive
- Very high resistance to cold and hot water as well as to saline solutions
- Excellent corrosion protection
- O-ring neutral

Application tips

For best adhesion, clean the surfaces mechanically first and then with OKS 2610/OKS 2611 universal cleaner. Spray on evenly OKS 341 spray. Allow excess to drip off and wait for lubricant to penetrate before resuming operation. Observe the machine manufacturer's instructions. Assess the lubrication frequencies and quantities on basis of service conditions, avoid excesses. Only mix with suitable lubricants.

Packaging

- 400 ml Spray

OKS 341

Chain Protector, highly adhesive, Spray

Technical data

	Standard	Conditions	Unit	Value
Main components				
base oil				polyisobutylene
additives				adhesion improver
additives				Mo _x -Active
Application related technical data				
marking	DIN 51 502			CLP X 460
viscosity (at 40°C)	DIN 51 562-1		mm ² /s	440
viscosity class	DIN ISO 3448	DIN 51 562-1, 40°C	ISO VG	460
flashing point	DIN ISO 2592	> 79	°C	> 200
lower operating temperature			°C	-30
upper operating temperature			°C	180
colour				greenish
density (at 20°C)	DIN EN ISO 3838		g/cm ³	0.67
four-ball test rig welding load	DIN 51 350-2		N	2,600
Properties and approvals				
UFI				0W21-80A9-U009-CTV0

OKS Spezialschmierstoffe GmbH

Ganghoferstraße 47

82216 Maisach

+49 8142 3051 - 500

info@oks-germany.com

www.oks-germany.com



The information in this publication reflects state-of-the-art technology, as well as extensive testing and experience. Due to the diversity of possible applications and technical realities, they can only serve as recommendations and are not arbitrarily transferable. Therefore, no obligations, liability or warranty claims can be derived from them. We only accept liability for the suitability of our products for particular purposes, and for certain properties of our products, in the event that we have accepted such liability in writing in the individual case. Any case of justified warranty claims shall be limited to the delivery of replacement goods free of defects, in the event that this subsequent improvement fails, to reimbursement of the purchase price. Any and all further claims, in particular the liability for consequential injuries or damage, shall always be excluded. Prior to use, the customer must conduct its own testing to prove suitability. The data are subject to change for the sake of progress. ® = Registered trademark
Product restricted to professional users. Safety data sheet available for download at www.oks-germany.com
 Our Customer and Technical service will be pleased to help should you have any further questions.