




OKS 255 Ceramic Paste



Description

All-purpose ceramic paste for lubricating and mounting heavily loaded sliding surfaces.

Applications

- Lubrication of all kinds of highly stressed sliding surfaces, especially at low slip speeds or with oscillating movements
- Surface separation of temperature-stressed threaded connections
- For stainless-steel connections

Branches

- Shipbuilding and marine technology
- Maintenance and servicing

Application tips

For best adhesion, clean contamination and other lubricants from thread and slide surfaces. Best way is to clean mechanically first (for example, with a wire brush) and then with OKS 2610/OKS 2611 universal cleaning agent. Use a brush, spatula or similar to apply evenly a suitable quantity of paste to the head or nut contact surface and to the thread. The paste also acts as a sealant against spray water and condensate. Do not use paste instead of grease and mix only with suitable lubricants.

Packaging

- 150 ml Dispenser
- 250 ml Brush tin
- 1 kg Can
- 5 kg Hobbock
- 25 kg Hobbock

Advantages and benefits

- Broad field of application
- Good wear and corrosion protection
- Prevents burning-on and cold welding
- Good pressure absorption capacity
- No classification marks according to (EG) No. 1272/2008
- Prolonged lubrication effect
- Metal-free



OKS 255

Ceramic Paste

Technical data

	Standard	Conditions	Unit	Value
Main components				
base oil				mineral oil
thickener				organic/inorganic
solid lubricants				white solid lubricants
additives				AW additives
additives				EP additives
Application related technical data				
drop point	DIN ISO 2176		°C	110
worked penetration	DIN ISO 2137		0.1 mm	290-330
oil separation	DIN 51 817	7d/40°C	percent in weight	< 1.5
lower operating temperature			°C	-30
upper operating temperature		lubrication	°C	100
upper operating temperature		separation	°C	1,400
colour				white
density	DIN EN ISO 3838	at 20°C	g/cm ³	0.93
water resistance	DIN 51 807-1	90°C	Degree	1-90
salt spray test	DIN EN ISO 9227	layer thickness 30 µm	h	> 500
four-ball test rig welding load	DIN 51 350-4		N	3,400
Total friction coefficient (µ)	DIN EN ISO 16 047	screw ISO 4017 M10x55-8.8 black-oxide, nut ISO 4032 M10-10 black-oxide		0.13

OKS Spezialschmierstoffe GmbH

Ganghoferstraße 47
82216 Maisach
+49 8142 3051 - 500
info@oks-germany.com
www.oks-germany.com

a brand of
 **FREUDENBERG**

The information in this publication reflects state-of-the-art technology, as well as extensive testing and experience. Due to the diversity of possible applications and technical realities, they can only serve as recommendations and are not arbitrarily transferable. Therefore, no obligations, liability or warranty claims can be derived from them. We only accept liability for the suitability of our products for particular purposes, and for certain properties of our products, in the event that we have accepted such liability in writing in the individual case. Any case of justified warranty claims shall be limited to the delivery of replacement goods free of defects, in the event that this subsequent improvement fails, to reimbursement of the purchase price. Any and all further claims, in particular the liability for consequential injuries or damage, shall always be excluded. Prior to use, the customer must conduct its own testing to prove suitability. The data are subject to change for the sake of progress. ® = Registered trademark
Product restricted to professional users. Safety data sheet available for download at www.oks-germany.com
Our Customer and Technical service will be pleased to help should you have any further questions.