





**OKS 1155**

**Adherent Silicone Grease**

**Technical data**

	Standard	Conditions	Unit	Value
<b>Main components</b>				
base oil				ester
base oil				polyphenylmethylsiloxane
thickener				lithium hydroxystearate
<b>Application related technical data</b>				
marking	DIN 51 502	DIN 51 825		MSI2R-60
viscosity (base oil)	DIN 51 562-1	at 25°C	mm <sup>2</sup> /s	100
drop point	DIN ISO 2176		°C	205
consistency	DIN 51 818	DIN ISO 2137	NLGI grade	2
worked penetration	DIN ISO 2137	60DH	0.1 mm	260-300
oil separation	DIN 51 817	18h/40°C	percent in weight	0.9
resistance to oxidation	DIN 51 808	100h/99°C	bar	< 1.0
lower operating temperature			°C	-65
upper operating temperature			°C	175
colour				beige
density	DIN EN ISO 3838	at 20°C	g/cm <sup>3</sup>	1.1
SKF-EMCOR	DIN 51 802		corr. degree	0
<b>Properties and approvals</b>				
UFI				U8X1-N075-V007-EMRT

**Klüber Lubrication München GmbH & Co. KG**  
Geisenhausenerstraße 7 / 81379 München /  
Germany / phone +49 89 7876-0

The data in this document is based on our general experience and knowledge at the time of publication and is intended to give information of possible applications to a reader with technical experience. It constitutes neither an assurance of product properties nor does it release the user from the obligation of performing preliminary field tests with the product selected for a specific application. All data are guide values which depend on the lubricant's composition, the intended use and the application method. The technical values of lubricants change depending on the mechanical, dynamical, chemical and thermal loads, time and pressure. These changes may affect the function of a component. We recommend contacting us to discuss your specific application. If possible we will be pleased to provide a sample for testing on request. Klüber products are continually improved. Therefore, Klüber Lubrication reserves the right to change all the technical data in this document at any time without notice.