



## **OKS 480**

# High-Pressure Grease, water-resistant, for Food Processing Technology



#### Description

Fully synthetic calcium sulphonate complex grease for high loads and pressures at applications in the complete food processing technology.

#### **Applications**

- Rolling and friction bearing lubrication, even at high temperatures
- Lubrication for bearings with contact to cleaning agents or disinfectants
- For mechanical units such as levers, joints and hinges, also under strong water effect

## **Branches**

- Catering equipment and food processing technology
- Chemical industry
- · Municipal services
- · Shipbuilding and marine technology
- · Plant and machine (tool) engineering
- Logistics
- Paper and packaging industry
- · Rail vehicle technology
- · Iron and steel industry
- · Rubber and plastic processing
- · Glass and foundry industry

## Advantages and benefits

- NSF H1 registered
- High shear stability prevents thinning out of the grease under extreme mechanical loads such as during vibrations
- Excellent wear protection and very good high-pressure properties
- The calcium sulphonate complex soap ensures excellent water resistance and very good corrosion protection
- Broad temperature application range (-30°C to +160°C)
- High temperature and oxidation stability through fully synthetic base oil
- Very high resistance to water-alkaline or acidic disinfectants and cleaning agents
- Also available as spray version OKS 481
- MOSH/MOAH-free (as per recipe)

### **Application tips**

Clean the lubricating points well for optimal effect. Before filling for first time, remove anti-corrosion agent. Fill the bearing such that all functional surfaces are certain of being greased. Fill normal bearings up to about 1/3 of the free space inside the bearing. Low-speed bearings (DN value below 50,000) and their housings should be filled completely. The bearing and machine manufacturer's instructions should be observed. Subsequent lubrication at the lubrication nipples by grease gun or by automatic lubrication system. Assess the lubrication frequency and quantity on the basis of the service conditions. If old grease cannot be removed, restrict the quantity of grease so as to avoid over-lubricating the bearing. If lubrication frequencies tend to be low, you should aim for a full grease change. Only mix with suitable lubricants.











# **OKS 480**

# High-Pressure Grease, water-resistant, for Food Processing Technology

## **Packaging**

400 ml Cartridge5 kg Hobbock1 kg Can25 kg Hobbock

#### **Technical data**

|   | Standard               | Conditions   | Unit       | Value                           |
|---|------------------------|--------------|------------|---------------------------------|
| Main components                         |                        |              |            |                                 |
| base oil                                |                        |              |            | polyalphaolefine                |
| thickener                               |                        |              |            | calcium sulphonate complex soap |
| Application related technical data      |                        |              |            |                                 |
| marking                                 | analogue to DIN 51 502 |              |            | KPHC2P-30                       |
| viscosity (base oil)                    | DIN 51 562-1           | at 40°C      | mm²/s      | 100                             |
| viscosity (base oil)                    | DIN 51 562-1           | at 100°C     | mm²/s      | 14.7                            |
| drop point                              | ASTM D2265             |              | °C         | > 300                           |
| consistency                             | DIN 51 818             | DIN ISO 2137 | NLGI grade | 2                               |
| worked penetration                      | DIN ISO 2137           | 60DH         | 0.1 mm     | 265-295                         |
| lower operating temperature             |                        |              | °C         | -30                             |
| upper operating temperature             |                        |              | °C         | 160                             |
| colour                                  |                        |              |            | beige                           |
| density                                 | DIN EN ISO 3838        | at 20°C      | g/cm³      | 0.99                            |
| DN value (dm x n)                       |                        |              | mm/min     | 400,000                         |
| four-ball test rig welding load         | DIN 51 350-4           |              | N          | 4,000                           |
| Properties and approvals                |                        |              |            |                                 |
| approval for food processing technology |                        |              |            | NSF H1, RegNr. 148971           |

## **OKS Spezialschmierstoffe GmbH**

Ganghoferstraße 47 82216 Maisach

**4** +49 8142 3051 - 500

☑ info@oks-germany.com

**#** www.oks-germany.com

a brand of



The information in this publication reflects state-of-the-art technology, as well as extensive testing and experience. Due to the diversity of possible applications and technical realities, they can only serve as recommendations and are not arbitrarily transferable. Therefore, no obligations, liability or warranty claims can be derived from them. We only accept liability for the suitability of our products for particular purposes, and for certain properties of our products, in the event that we have accepted such liability in writing in the individual case. Any case of justified warranty claims shall be limited to the delivery of replacement goods free of defects, in the event that this subsequent improvement fails, to reimbursement of the purchase price. Any and all further claims, in particular the liability for consequential injuries or damage, shall always be excluded. Prior to use, the customer must conduct its own testing to prove suitability. The data are subject to change for the sake of progress. \*\* = Registered trademark\*\*

Product restricted to professional users. Safety data sheet available for download at www.oks-germany.com Our Customer and Technical service will be pleased to help should you have any further questions.





