



OKS 200

MoS₂ Assembly Paste



Mo_x - Active

Description

OKS 200 is a MoS₂-paste for assembly lubrication for press-on processes.

Applications

- Mounting paste for press-fitting wheels, shafts, tires or bearings to prevent galling
- Non-stick primer coat for moving threads, supports, guides and slideways to prevent stick-slip effect
- Wearing-in lubrication of highly stressed sliding surfaces such as plain bearings, gearwheels, crankshafts with provision of anti-seizing properties
- In non-cutting shaping of the difficult type, such as doming, pressing, embossing while avoiding critical metal contacts and welding

Advantages and benefits

- Against seizing, wear and stick-slip
- Highly effective due to the strong affinity of the MoS₂ for metals
- Extremely low friction at highest loading capability
- Increased operational reliability of moving parts due to anti-seizing properties
- Resistant to water, oil, grease, chemicals and hydraulic media
- Improved performance due to organic molybdenum complex compounds

Branches

- Plant and machine (tool) engineering
- Iron and steel industry
- Chemical industry
- Glass and foundry industry
- Rail vehicle technology
- Municipal services
- Logistics
- Rubber and plastic processing
- Shipbuilding and marine technology
- Paper and packaging industry

Application tips

For best adhesion, clean the surfaces from dirt and other lubricants. Best way is to clean mechanically first and then with OKS 2610 or OKS 2611 universal cleaner. Apply paste evenly thin with brush, spatula, etc. Remove excessing paste. Do not use paste instead of grease and only mix with appropriate lubricants.

Packaging

- 40 ml Tube
- 250 g Can
- 1 kg Can
- 5 kg Hobbock
- 25 kg Hobbock



OKS 200
MoS₂ Assembly Paste

Technical data

	Standard	Conditions	Unit	Value
Main components				
base oil				synthetic oil
thickener				lithium soap
solid lubricants				white solid lubricants
solid lubricants				MoS ₂
solid lubricants				graphite
additives				Mo _x -Active
Application related technical data				
unworked penetration	DIN ISO 2137	no shear stress	0.1 mm	220-250
lower operating temperature			°C	-35
upper operating temperature		separation	°C	450
colour				black
density	DIN EN ISO 3838	at 20°C	g/cm ³	1.2
four-ball test rig welding load	DIN 51 350-4		N	2,400
Total friction coefficient (μ)	DIN EN ISO 16 047	screw ISO 4017 M10x55-8.8 black-oxide, nut ISO 4032 M10-10 black-oxide		0.07
breakaway torque	DIN 267-27	M10 A2, 40 Nm, 400 °C, 100 h	Nm	< 2,0 x tightening torque
press-fit test (μ)	draft DIN 51 833			0,09, no chatter
Properties and approvals				
UFI				SJ49-30GQ-H00E-YJEM

Klüber Lubrication München GmbH & Co. KG
Geisenhausenerstraße 7 / 81379 München /
Germany / phone +49 89 7876-0

The data in this document is based on our general experience and knowledge at the time of publication and is intended to give information of possible applications to a reader with technical experience. It constitutes neither an assurance of product properties nor does it release the user from the obligation of performing preliminary field tests with the product selected for a specific application. All data are guide values which depend on the lubricant's composition, the intended use and the application method. The technical values of lubricants change depending on the mechanical, dynamical, chemical and thermal loads, time and pressure. These changes may affect the function of a component. We recommend contacting us to discuss your specific application. If possible we will be pleased to provide a sample for testing on request. Klüber products are continually improved. Therefore, Klüber Lubrication reserves the right to change all the technical data in this document at any time without notice.