


## OKS 217

### High-Temperature Paste, High purity



#### Description

OKS 217 is a high-temperature paste

#### Applications

- Assembly lubrication of screw connections of high-strength steel subject to high temperatures, corrosive influences in chemically aggressive environments, e.g. on gas and steam turbines in power plants, combustion engines, threads on pipe fittings, flange joints and fittings in superheated steam lines, exhaust pipe and combustion chamber screwed connections etc.
- Parting lubrication of materials with a tendency to seize up, e.g. V2A, V4A and high-temperature steels

#### Branches

- Paper and packaging industry
- Shipbuilding and marine technology
- Glass and foundry industry
- Logistics
- Plant and machine (tool) engineering
- Rubber and plastic processing
- Chemical industry
- Municipal services
- Iron and steel industry
- Rail vehicle technology

#### Application tips

For best adhesion, clean the threads and sliding surfaces from dirt and other lubricants. Best way is to clean mechanically first and then with OKS 2610 or OKS 2611 universal cleaner. Apply paste evenly in sufficient amount onto head/nut support and thread or onto the sliding areas with brush, spatula, etc. Paste also takes over sealing properties. Do not use paste instead of grease and mix with appropriate lubricants only.

#### Packaging

- 250 g Brush tin
- 1 kg Can
- 5 kg Hobbock

#### Advantages and benefits

- Excellently suited for preventing seizing and binding
- Highly effective against corrosion affects
- Free of lead compounds, sulphides, chlorides and fluorides

# OKS 217

## High-Temperature Paste, High purity

### Technical data

	Standard	Conditions	Unit	Value
<b>Main components</b>				
base oil				semi-synthetic oil
<b>Application related technical data</b>				
drop point	DIN ISO 2176		°C	without
unworked penetration	DIN ISO 2137	no shear stress	0.1 mm	280-310
lower operating temperature			°C	-40
upper operating temperature		separation	°C	1,400
colour				dark-grey
density	DIN EN ISO 3838	at 20°C	g/cm <sup>3</sup>	1.27
water resistance	DIN 51 807-1	3h/90°C	Degree	1-90
four-ball test rig welding load	DIN 51 350-4		N	4,400
Total friction coefficient (μ)	DIN EN ISO 16 047	screw ISO 4017 M10x55-8.8 black-oxide, nut ISO 4032 M10-10 black-oxide		0.11
Total friction coefficient (μ)	DIN EN ISO 16 047	Screw ISO 4017 A4 M10x55-70, Nut ISO 4032 A4 M10-70		0.16
breakaway torque	DIN 267-27	M10 A4, 40 Nm, 400 °C, 100 h		< 2,0 x tightening torque
press-fit test (μ)	draft DIN 51 833			0,11, chatter from 4,000 N on
<b>Properties and approvals</b>				
UFI				YY7D-G0MH-G005-TWU2

**Klüber Lubrication München GmbH & Co. KG**  
 Geisenhausenerstraße 7 / 81379 München /  
 Germany / phone +49 89 7876-0

The data in this document is based on our general experience and knowledge at the time of publication and is intended to give information of possible applications to a reader with technical experience. It constitutes neither an assurance of product properties nor does it release the user from the obligation of performing preliminary field tests with the product selected for a specific application. All data are guide values which depend on the lubricant's composition, the intended use and the application method. The technical values of lubricants change depending on the mechanical, dynamical, chemical and thermal loads, time and pressure. These changes may affect the function of a component. We recommend contacting us to discuss your specific application. If possible we will be pleased to provide a sample for testing on request. Klüber products are continually improved. Therefore, Klüber Lubrication reserves the right to change all the technical data in this document at any time without notice.